

**PRODUCT DESCRIPTION** A two pack foul release system linkcoat.

**INTENDED USES** To enable application of the Intersleek 700 and Intersleek 900 Foul Release Systems over a wide range of existing antifoulings.  
For use at Newbuilding and Maintenance & Repair.

**PRODUCT INFORMATION**

<b>Colour</b>	BXA727-Red Brown
<b>Finish/Sheen</b>	Matt
<b>Part B (Curing Agent)</b>	BXA728
<b>Volume Solids</b>	56% ±2% (ISO 3233:1998)
<b>Mix Ratio</b>	4 volume(s) Part A to 1 volume(s) Part B
<b>Typical Film Thickness</b>	100 microns dry (179 microns wet)
<b>Theoretical Coverage</b>	5.60 m <sup>2</sup> /litre at 100 microns dft, allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Brush, Roller
<b>Flash Point</b>	Part A 45°C; Part B 21°C; Mixed 38°C
<b>Induction Period</b>	Not required

<b>Drying Information</b>	10°C	15°C	25°C	35°C
Touch Dry [ISO 1517:73]	6 hrs	4 hrs	3 hrs	2.5 hrs
Hard Dry [ISO 9117:90]	20 hrs	16 hrs	9 hrs	5 hrs
Pot Life	12 hrs	10 hrs	6 hrs	4 hrs

<b>Overcoating Data - see limitations</b>	<b>Substrate Temperature</b>							
	10°C		15°C		25°C		35°C	
<b>Overcoated By</b>	Min	Max	Min	Max	Min	Max	Min	Max
Intersleek 731	-	-	-	-	6 hrs	5 days	4 hrs	5 days
Intersleek 737	6 hrs	5 days	6 hrs	5 days	6 hrs	5 days	4 hrs	5 days

**REGULATORY DATA**

<b>VOC</b>	429 g/lit as supplied (EPA Method 24) 308 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)
------------	--

**Note:** VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

**SYSTEMS AND  
COMPATIBILITY**

Consult your International Paint representative for the system best suited for the surfaces to be protected.

---

**SURFACE PREPARATIONS**

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

The leached layer from the existing antifouling must be removed prior to application of Intersleek 7180. To do this it is recommended to use high pressure freshwater >3,500 psi (>220 bar) and fan lances. If the leached layer cannot be fully removed at >3,500 psi (220 bar) then pressures of up to 5,000psi (314 bar) may be required.

Intersleek 7180 should always be applied over an approved antifouling and/or anticorrosive scheme. Areas of breakdown, damage etc. should be prepared to the specified standard (eg. Sa2½ (ISO 8501-1:2007)) and patch primed with Intershield 300. The Intersleek 7180 link coat scheme should then be applied over all.

Consult your International Paint representative for specific recommendations.

**NOTE**

**For use in Marine situations in North America, the following surface preparation standards can be used:  
SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)**

**APPLICATION**

<b>Mixing</b>	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified. (1) Agitate Base (Part A) with power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.
<b>Thinner</b>	Use International GTA220. Do not thin more than allowed by local environment legislation.
<b>Airless Spray</b>	Recommended Tip Range 0.46-0.66 mm (18-26 thou) Total output fluid pressure at spray tip not less than 176 kg/cm <sup>2</sup> (2500 p.s.i.)
<b>Brush</b>	Application by brush is recommended for small areas only.
<b>Roller</b>	Application by roller is recommended for small areas only.
<b>Cleaner</b>	International GTA822
<b>Work Stoppages and Cleanup</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
<b>Welding</b>	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

**SAFETY**

**All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**

**Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.**

**EMERGENCY CONTACT NUMBERS:**

**USA/Canada - Medical Advisory Number 1-800-854-6813**

**Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191**

**China – Contact (532) 838 89090 Shanghai - Contact (21) 626 79090**

**R.O.W. - Contact Regional Office**

**LIMITATIONS**

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather when air and surface temperatures are above 10°C. Intersleek 7180 cannot be used below 10°C. The temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with the information given in the STORAGE section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application guidelines. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results actually found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 lt	16 lt	20 lt	4 lt	5 lt

For availability of other unit sizes consult International Paint


UNIT SHIPPING WEIGHT	Unit Size	Unit Weight
	20 lt	30.44 Kg

STORAGE	Shelf Life	12 months at 25°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

**WORLDWIDE AVAILABILITY** Consult International Paint.

**IMPORTANT NOTE**

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

 **International** and product names mentioned in this data sheet are trademarks of, or are licensed to, AkzoNobel.

© AkzoNobel, 2010

[www.international-marine.com](http://www.international-marine.com)